

PRODUCT DATA SHEET

Sika® Fibermesh®-300

MICRO-SYNTHETIC FIBRILLATED FIBER

PRODUCT DESCRIPTION

Sika® Fibermesh®-300, micro-reinforcement system for concrete is made up of 100 percent virgin homopolymer polypropylene fibrillated fibers with e3 patented technology containing no reprocessed olefin materials. Specifically engineered and manufactured in an ISO 9001 certified manufacturing facility for use as concrete reinforcement. Sika® Fibermesh®-300 previously SikaFiber PPF.

USES

Sika® Fibermesh®-300 is a micro fiber that acts mechanically by supporting the aggregate within the concrete with multidimensional fiber network and helps to develop a uniform bleed in the concrete system. The fiber does not affect the curing process chemically and it does not absorb water. The Sika® Fibermesh®-300 can be used in all types of concrete applications to control plastic shrinkage and settlement cracking. Typical applications include:

- Residential applications: sidewalks, driveways, decks, curbs
- Stucco
- Shotcrete
- Overlays & toppings
- Roads & pavements
- Tanks & pools

PRODUCT INFORMATION

Packaging

Sika® Fibermesh®-300 is available in a variety of packaging options. The bags are packed into cartons and palletized.

Appearance / Color

- **Fiber Type:** Fibrillated micro synthetic fiber
- **Fiber Network:** 185,000 fibers / lb (408,000 fibers / kg)

Shelf Life

When stored in dry conditions, shelf life is 5 years.

CHARACTERISTICS / ADVANTAGES

- Reduces plastic shrinkage and settlement cracking.
- Replacement for typical light gauge wire mesh - 6x6 W1.4/W1.4 (152x152 MW9.1/MW9.1)
- Improves impact, shatter and abrasion resistance
- Enhances durability
- Promotes uniform bleed and reduces bleed water
- Inhibits and controls the formation of intrinsic cracking in the concrete
- Reinforces against abrasion
- Reduces freeze / thaw damage
- Increases cohesion and reduces segregation

APPROVALS / STANDARDS

- Complies with European Standard EN 14889-2:2006 Fibres for Concrete Part 2: Class Ia and carries the CE marking.
- UL/ULC Classification: For use as an alternate or in addition to the welded wire fabric used in floor-Ceiling D700, D800, D900, G229, G243, G256, & G514 Series Designs.
- Complies with ASTM C1116/ C1116M, Type III fiber reinforced concrete and therefore ASTM D7508.

Storage Conditions	Sika® Fibermesh®-300 should be stored in a dry warehouse. Protect product from the rain and direct sunlight.
Dimensions	<ul style="list-style-type: none"> ▪ Length: Graded 0.5 & 0.75 inches (12.7 & 19 mm). Also available in single cut lengths. ▪ Diameter: 0.01, 0.015, & 0.025 inches (0.24, 0.4, & 0.64 mm). Also available in single equivalent diameter. ▪ Aspect Ratio: Varies from 20 to 79
Melting Point	324 °F (162 °C)

TECHNICAL INFORMATION

Resistance to Alkalinity	Excellent
---------------------------------	-----------

APPLICATION INFORMATION

Recommended Dosage	The dosage of Sika® Fibermesh®-300 will vary according to the type of application and performance requirements. Standard recommended dosage rate of Sika® Fibermesh®-300 is 1.5 to 3 lb/cu yd (0.89 to 1.8 kg/m³) of concrete. Dosages outside the recommended dosage can be used to meet project specific requirements. If this is the case please contact your Sika representative for technical support.
---------------------------	---

Mixing	<p>Sika® Fibermesh®-300 in degradable bags can be added directly to the concrete mixing system after the batching of the other ingredients and mixed for 4 to 5 minutes or 70 revolutions.</p> <p>Application The addition of Sika® Fibermesh®-300 at the normal recommended dosage rate does not require any mix design or application changes. The fiber concrete can be mixed, sprayed or placed using conventional equipment.</p> <p>Tooling & Finishing Sika® Fibermesh®-300 can be finished by most finishing techniques as indicated in ACI-302.</p>
---------------	---

BASIS OF PRODUCT DATA

Results may differ based upon statistical variations depending upon mixing methods and equipment, temperature, application methods, test methods, actual site conditions and curing conditions.

OTHER RESTRICTIONS

See Legal Disclaimer.

ENVIRONMENTAL, HEALTH AND SAFETY

For further information and advice regarding transportation, handling, storage and disposal of chemical products, user should refer to the actual Safety Data Sheets containing physical, environmental, toxicological and other safety related data. User must read the current actual Safety Data Sheets before using any products. In case of an emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

LEGAL DISCLAIMER

- KEEP CONTAINER TIGHTLY CLOSED
- KEEP OUT OF REACH OF CHILDREN
- NOT FOR INTERNAL CONSUMPTION
- FOR INDUSTRIAL USE ONLY
- FOR PROFESSIONAL USE ONLY

Prior to each use of any product of Sika Corporation, its subsidiaries or affiliates ("SIKA"), the user must always read and follow the warnings and instructions on the product's most current product label, Product Data Sheet and Safety Data Sheet which are available at usa.sika.com or by calling SIKA's Technical Service Department at 1-800-933-7452. Nothing contained in any SIKA literature or materials relieves the user of the obligation to read and follow the warnings and instructions for each SIKA product as set forth in the current product label, Product Data Sheet and Safety Data Sheet prior to use of the SIKA product.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within the product's shelf life. User determines suitability of product for intended use and assumes all risks. User's and/or buyer's sole remedy shall be limited to the purchase price or replacement of this product exclusive of any labor costs. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Sale of SIKA products are subject to the Terms and Conditions of Sale which are available at <https://usa.sika.com/en/group/SikaCorp/termsandconditions.html> or by calling 1-800-933-7452.

Sika Corporation

201 Polito Avenue
Lyndhurst, NJ 07071
Phone: +1-800-933-7452
Fax: +1-201-933-6225
usa.sika.com

Sika Mexicana S.A. de C.V.

Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Product Data Sheet

Sika® Fibermesh®-300
November 2019, Version 01.01
021408021010000142

SikaFibermesh-300-en-US-(11-2019)-1-1.pdf

